

Oscura™ Blackened Steel

Oscura Blackened Steel is a rich, blackened patina on steel developed for interior use. Activated steel surfaces create a mottled and artistic ambiance that varies from sheet to sheet. Developed as a finish for interior feature walls, lobbies, perforated metal features, and other design accents, Oscura creates a tapestry of black and gray hues that can complement a wide range of materials and colors.

MAIN FEATURES AND CHARACTERISTICS

Sealed with a clear coat to protect against scratches, scrapes, and rusting caused by the ambient interior environment.

- Produced using environmentally friendly manufacturing practices in our award-winning, EPA-compliant facility.
- Availability in a wide variety of sheet thicknesses, sizes and order quantities to fit almost any project and budget.
- 100% metal construction means a familiar and common fabrication techniques, a non-combustible surface, and easy recyclability at end-of-life.

AVAILABLE ALLOYS, THICKNESSES AND SIZES

Oscura Blackened Steel is available as a single-sided product in a variety of sheet thicknesses and sizes.

Refer to the table below for more detailed information.

OSCURA BLACKENED STEEL - THICKNESS AND SIZE AVAILABILITY

Thicknesses	Sheet Sizes					
	4' x 8'	4' x 10'	4' x 12'	5' x 8'	5' x 10'	5' x 12'
20 ga [0.038"]						not available
18 ga [0.050"]	available single-sided only					
16 ga [0.063"]	available single-sided only					
14 ga [0.078"]						not available
12 ga [0.109"]						not available
11 ga [0.125"]						not available
3/16" [0.188"]	not available					

DIMENSIONS AND TOLERANCES

Dimensional tolerances for Oscura Blackened Steel are provided in the table below.

OSCURA BLACKENED STEEL - DIMENSIONAL TOLERANCES

Property	Unit	Value
Width	in	+1/8, -0
Length	in	+3/8, -0
Flatness ¹	in	0.4

¹ Maximum deviation from a horizontal, flat surface.

PATTERN AND COLOR

Oscura Blackened Steel is made to order by Zahner artisans, using an accelerated patination process that results in an oxide layer that is subject to natural variations in color and pattern.

No two sheets of are identical. If anticipating the need for additional sheets in the future, it is recommended to order these at the time of initial order to minimize batch-to-batch variation.

MATERIAL AND PHYSICAL PROPERTIES

Oscura Blackened Steel is a cold-rolled steel. Select material and physical properties are presented in the table below.

OSCURA BLACKENED STEEL - SELECT MATERIAL AND PHYSICAL PROPERTIES

Property	Unit	Value
Density	lbs/ft ³	491
Coefficient of Thermal Expansion	in/in/°F	7.0×10^{-6}

FLAMMABILITY

Oscura Blackened Steel is 100% monolithic steel and is a non-combustible material.

OUTDOOR USE AND LIMITATIONS

Oscura Blackened Steel can only be used in interior applications, should not be used near water or wet environments, and should be installed in areas subject to climate controlled conditions.

FABRICATION GUIDELINES

Please follow the below guidelines for fabricating sheets of Oscura Blackened Steel.

General notes for all fabrication

- Follow best-practices in regards to proper occupational health and safety measures, such as the wearing of eye protection, and the use of respirator devices when grinding or polishing.
- Prior to fabrication for your project, it is strongly recommended that any fabrication steps be tested on sample material or fall-off.

Cutting and Drilling

Use High Speed Steel, Heavy Duty Machine Drill bits at the proper speed when drilling holes.

Oscura Blackened Steel may be cut using a shear for simple linear cuts. The use of cardboard or other surface protection measures are recommended to protect the surface from oils and other debris.

For the cutting of simple curves and forms, manual cutting

methods appropriate for steel, eg, a cutting wheel, or jigsaw with the proper blade, will suffice.

For the cutting of complex and/or detailed shapes, CNC methods, such a laser cutting machine capable of cutting steel, or plasma, is recommended. For appropriate cutting parameters (speed, power, etc), please reference the manufacturer's recommended settings for steel.

Bending

Oscura Blackened Steel can be bent to a variety of forms using commonly practiced sheet-metal bending techniques. To maintain the appearance of the Oscura Blackened Steel surface, the following best-practices are recommended:

- DO use a brake-press with a properly sized punch and die.
- DO use Rhino Hide or an equivalent aid to protect the surface.
- DO NOT bend to an outside radius less than 2.5x the thickness of the sheet.

Welding and Soldering

Oscura Blackened Steel is compatible with all steel welding methods, including stud welding techniques.

Note that the surface of the welds will not match the Oscura finish. Therefore, it is recommended that designs that require welding take this into account and locate the welds where they will be hidden from view.

Gluing

Oscura Blackened Steel is compatible with a variety of common adhesives designed for metals. Follow the manufacturer's recommended procedures for steel/metal when bonding Oscura Blackened Steel to other materials.

STORAGE AND HANDLING

Oscura Blackened Steel should be stored in its original packaging in a dry, indoor location away from direct sunlight. Store the product on flat, level ground. Keep in a low-traffic location to help protect all edges from incidental damage. Any protective masking, if applied, should be removed within 6 months of the date of shipment.

- Do not store outside, in direct sunlight, or in wet environments.
- Do not stack objects on top of the products or packaging.

END OF LIFE AND DISPOSAL

Oscura Blackened Steel is 100% monolithic steel and can be recycled at end of life using the existing scrap and recycling streams for metals.

Handling

When handling Oscura Blackened Steel, the wearing of cotton, nitrile or latex gloves is recommended to prevent dirt and oils from contaminating the finish. When carrying or manually transporting, take all necessary precautions to prevent denting, scratching or other damage to the finish. If temporarily setting sheets of Oscura Blackened Steel on an edge, the use of wood blocking and/or shop towels is recommended between the sheet's edge and the ground in order to prevent denting or deforming of the edge.

CLEANING

Clean Oscura Blackened Steel only when required to remove dirt, dust or other visible surface debris. Excessively frequent cleaning can wear away the factory-applied clear coat, requiring re-application to prevent unwanted oxide development (see 'Refinishing' section below).

To clean, use warm soapy water and a clean, soft cotton cloth, followed by a thorough rinse using clean water. Immediately wipe dry with a clean, soft cotton cloth. Do not allow water to remain on the surface.

If a more aggressive cleaning solution is required, Isopropyl Alcohol, Windex® Original Glass Cleaner, or Windex Vinegar Glass Cleaner can also be used. Clean and immediately wipe dry with a clean, soft cotton cloth.

Whenever cleaning Oscura Blackened Steel for the first time, test in an inconspicuous area. If a successful result is obtained, cleaning the rest of the surface can begin.

REFINISHING

Oscura Blackened Steel is factory-sealed with a clear coat to protect against minor scratches, scrapes, and rusting caused by a humid ambient interior environment.

Annual re-application of a clear coat is recommended to maintain Oscura's initial appearance. Griot's Speed Shine® is recommended to restore the surface clear coat to its factory condition.